



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 : C23C 4/12		(11) International Publication Number: WO 00/00660
A1		(43) International Publication Date: 6 January 2000 (06.01.00)
(21) International Application Number: PCT/US99/14912 (22) International Filing Date: 30 June 1999 (30.06.99) (30) Priority Data: 09/106,456 30 June 1998 (30.06.98) US (71) Applicants: UNIVERSITY OF CONNECTICUT [US/US]; 263 Farmington Avenue, MC-5355, Farmington, CT 06030-5355 (US). THE GOVERNMENT OF THE UNITED STATES OF AMERICA , represented by THE SECRETARY OF THE NAVY [US/US]; Naval Research Laboratory, 4555 Overlook Avenue, S.W., Washington, DC 20375-5325 (US). (72) Inventors: CHOW, Gan-Moog; 113 Clementi Road, Block D, No. 05-05, Singapore 129793 (SG). KURIHARA, Lynn, K.; 7518 C. Snowpea Court, Alexandria, VA 22306 (US). XIAO, T., Danny; 99 Walden Apartments, 70 Piney Hill Road, West Willington, CT 06279 (US). STRUTT, Peter, R.; 126 Clover Mill Road, Storrs, CT 06268 (US). STROCK, Chistopher, W.; 76 Wildwood Road, Storrs, CT 06268 (US). ZATORSKI, Raymond, A.; 77 Wapawag Road, East Hampton, CT 06268 (US). KEAR, Bernard; 10 Campbell Brook Road, Whitehouse Station, NJ 08889 (US).		(74) Agent: REIMER, Leah, M.; Cantor Colburn LLP, 88 Day Hill Road, Windsor, CT 06095 (US). (81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published With international search report.
(54) Title: NANOSIZE PARTICLE COATINGS MADE BY THERMALLY SPRAYING SOLUTION PRECURSOR FEEDSTOCKS		
<p>The graph plots 'PERCENT OF A AND B' on the y-axis (0% to 100%) against 'INCREASING DISTANCE FROM S' on the x-axis (1 to 5). Curve A starts at 100% at distance 1 and decreases to 0% at distance 3. Curve B starts at 0% at distance 1 and increases to 100% at distance 3, then decreases back to 0% at distance 5.</p>		
(57) Abstract		
<p>Thin films or coatings having a thickness of about 100 nanometers or larger are made of nanostructured particles which have a particle size less than 100 nm (i.e. 0.1 micron) by thermally spraying a solution of a liquid coating precursor feedstock onto a substrate to form the film or coating. By thermal spraying with different precursor feedstock solutions, coatings can be made with more than one layer. Also, by varying the composition of the precursor feedstock during spraying, a fine composition gradient coating can be formed which is made up of the same small nanoparticle size particles of less than 100 nm. Many combinations of materials can be co-deposited and by applying an external energy source either during the coating process or during post deposition, the resulting coating can be modified.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

NANOSIZE PARTICLE COATINGS MADE BY THERMALLY SPRAYING SOLUTION PRECURSOR FEEDSTOCKS

Background of the Invention

1. Field of the Invention

This invention relates to a thermal spray process which uses solution precursors as a feedstock.

5 2. Description of the Related Art

Coatings are commonly used to provide desirable surface properties of the underlying bulk substrates. Examples of protective coatings include wear-resistant, corrosion-resistant and thermal barrier coatings. In many applications, multiple properties of the coatings are often desirable. However, it is not always possible to have
10 a single material (single phase material, alloy or composite) that has all the required properties. In such a case, multiple materials with different properties can be used in the form of multilayers.

Conventional coatings, including multilayered coatings, are made of coarse-grained materials with grain sizes which are greater than several microns. These
15 coatings can be prepared by solution chemistry, physical or chemical vapor deposition or thermal spraying. For deposition methods that do not involve solution based chemistry, physical vapor methods such as sputtering and beam induced evaporation are commonly used. The vapor of the materials (as atoms or clusters) condense on the substrate to form coatings. The chemical vapor approach generally involves pyrolysis

of chemical precursors at the substrate to form desirable reaction product coatings. Vapor techniques are generally suitable for preparing thick films or thin coatings due to the low rate of deposition.

An alternative approach to fabrication of thick coatings is thermal spraying. In thermal spraying powders are generally used as the feedstock and fed into a flame aimed at the surface of substrates. The powders are propelled in the gas flow and are fused to form coatings on the substrate. Thermal spraying includes plasma methods in the ambient atmosphere or vacuum, high velocity oxyfuel spraying or high velocity impact fusion spraying. In all cases, the feedstock are often very coarse agglomerates of powders. The agglomerate size is typically in the tens of microns. The powder agglomerates often form splat microstructures, which are pancake-like structures in the thermally sprayed coatings.

Although thermal spraying is a viable approach to preparing thick coatings, the use of the powder agglomerate feedstock has limitations and problems. First, the sprayable powders often require reprocessing from the parent powders by controlled agglomeration, which adds more cost to the production and often introduces impurities if surface-active precursors are used as binders. Second, the splat boundaries in the as-sprayed coatings are often the initiation sites for flaw propagation that consequently lead to mechanical failure of the coatings. Third, the as-formed splat microstructures present a limitation on the scale of chemical homogeneity and mixing of multiphasic materials when desired because the splat is at least greater than several microns thick, due to the flattening of the molten particles on impact. From commercial experience, sprayable powders need to be of a certain size such as about 30 microns or larger for efficient deposition. As a result, reconstitution of nanoscale powder to 30 micron-sized agglomerates is often required. Unfortunately, these larger diameter agglomerates produce longer splat microstructures in the coating. These large splat particles become a serious problem when multifunctional applications require multilayered, hybrid coatings with fine, continuous interfaces, since the length scale of an interface is limited by the splat microstructure.

To solve this fine gradient coating problem, we proposed to use liquid solutions wherein the composition of the solution is varied as the coating is applied. Although it has been known to use a liquid feedstock in thermal spraying, such disclosures do not relate to the production of nanostructure coatings and the multilayer and gradient
5 coatings of the present invention.

U.S. Patent No. 5,032,568 to Lau *et al* uses an atomized aqueous solution containing at least 3 metal salts precursors into an inductively coupled ultra high temperature plasma for coating. There is no discussion of forming nanostructure coatings nor of how to provide multilayer and gradient coatings on such a small scale.

10 U.S. Patent No. 4,982,067 to Marantz *et al* relates to an apparatus to eliminate the long-standing problems with radial feed plasma spray apparatus by designing a true axial feed in a plasma spray system. While most of this disclosure is to using particles as the feed, at column 5, lines 51-55, the patent states that "alternatively, the feedstock may be in liquid form, such as a solution, a slurry or a sol-gel fluid, such that the liquid
15 carrier will be vaporized or reacted off, leaving a solid material to be deposited." Again, there is no discussion of forming nanostructure coatings nor of how to provide multilayer and gradient coatings on this small scale. In addition this patent essentially deals with the deposition of solid particles that are formed by conversion of the droplets to solid particles in flight before impacting the substrate.

20 U.S. 5,413,821 to Ellis *et al* relates to an inductively coupled plasma to thermally decompose a chromium bearing organometallic compound. Column 2, lines 19-22, states that the organometallic compound can be introduced to the plasma as a vapor or a solid. However, in Example 4 the tetra-methylchromium is cryogenically cooled to the liquid state for application to the plasma coating device. The
25 organometallic liquid was introduced into the plasma by bubbling through a carrier gas or in the form of solid powder entrained in the carrier gas. The former may actually exist in the form of chemical vapor. Again, there is no discussion of forming nanostructure coatings nor of how to provide multilayer and gradient coatings on this small scale.

U.S. 5,609,921 to Gitzhofer *et al* discloses a suspension plasma spray where a suspension of particles of the material to be deposited is in a liquid or semi-liquid carrier substance. An inductively coupled radio-frequency plasma torch is used. The preformed particles are suspended in a liquid carrier. Vaporization of the liquid carrier
5 in the plasma leads to the agglomeration of the particles. The particles become molten and impact the substrate. Suspension of small particles in a liquid and its subsequent spraying into the plasma flame may lead to an additional problem. If the particles are dispersed and are very fine (such as less than 100 nm), they may not have enough momentum to penetrate into the plasma flame and be carried by the plasma flame to the
10 substrate. Again, there is no discussion of forming nanostructure coatings nor of how to provide multilayer and gradient coatings on this small scale.

Summary of the Invention

It is an object of this invention to use of solution precursors as feedstock in thermal spraying of ceramic, metallic, organic and hybrid (a combination of various
15 classes of materials) coatings in a potentially competitive, single step fabrication process for coatings.

It is a further object of this invention to provide a thermal spray process which eliminates the need to synthesize powders and reprocess these powders for spraying.

It is a further object of this invention to utilize the chemical conversion of
20 droplets in a thermal spray process to form desirable reaction products as coatings on substrates in a single step synthesis process.

It is a further object of this invention to provide a thermal spray process in which solution feedstocks are employed for better homogeneity and mixing of multiphasic materials.

25 It is a further object of this invention to reduce costs for preparing coatings of high melting temperature materials by replacing the melting of the powder required in conventional thermal spray of powder feedstock with the lower temperature solidification of thermally sprayed droplets at the substrate.

It is a further object of this invention to utilize the molecular design of solution
30 precursors for desirable reaction products in a thermal spray process.

It is a further object of this invention to utilize an external energy source simultaneously during the thermal spraying to affect the molecular design, structure, microstructure and interfaces of the coating.

It is a further object of this invention to utilize a post deposition application of
5 an external energy source to further affect the molecular design, microstructure and interfaces of the coating.

It is a further object of this invention to employ a thermal spray process with a solution feedstock in which the droplet size is varied.

It is a further object of this invention when using a thermal spray process with a
10 solution feedstock to further reduce droplet size by placing a fine screen mesh between the spray nozzle and the substrate.

It is a further object of this invention when using a thermal spray process with a solution feedstock to control the residence time, the in-flight temperature of droplet, and the working distance to the substrate to control the structure and the microstructure
15 of the deposited coatings.

It is a further object of this invention to employ a thermal spray process in which fine droplets are allowed to solidify before reaching the substrate by controlling the in-flight temperature so that the resulting splat will have a smaller dimension compared to that obtained by using a powder feedstock.

It is a further object of this invention to employ a thermal spray process in
20 which droplets are allowed to reach the substrate in the liquid state so that solidification of droplets at the substrate will also lead to finer splat microstructure and better chemical mixing when more than a single phase of materials are sprayed.

It is a further object of this invention to employ a thermal spray process that is
25 suitable for producing multilayered materials that require fine scale grading, both compositionally and microstructurally, and particularly for nanostructured graded materials.

It is a further object of this invention to employ a thermal spray process which permits the integration of layers by gradually graded interfaces rather than abrupt

interfaces so as to permit the compatibility of hybrid multilayered materials, i.e. ceramics-ceramics; metal-ceramics; metal-metal, organic-inorganic; and in any combination.

It is a further object of this invention to employ a thermal spray process which
5 permits microstructural, structural and chemical grading with continuous interfaces at a fine scale.

It is a further object of this invention to employ a thermal spray process in which the process can be adapted to contain nanostructured pre-formed particles in
10 solution so that the solution provides the percolating matrix whereas the powders provide the major constituents of the coating layers.

These and further objects of the invention will become apparent as the description of the invention proceeds.

It has now been found that thin films or coatings can be made of nanostructured
15 particles which have a particle size less than 100 nm (i.e. 0.1 micron) by thermally spraying a solution of a liquid coating precursor feedstock onto a substrate to form the film or coating. The resulting thin film or coating has a thickness of about 100 nanometers or larger. By using thermal spraying with different precursor feedstock solutions, coatings can be made with more than one layer. Within a given layer, by
20 varying the composition of the precursor feedstock, a composition gradient coating can be formed having nanoparticle size particles of less than 100 nm. Many combinations of materials can be co-deposited, such as ceramics-ceramics, metal-ceramics, metal-metal, and organic-inorganic. By applying an external energy source either during the coating process or during post deposition, the resulting coating can be modified.

25 A further feature of the invention is that multifunctional, multilayered, nanostructured coatings can be better prepared by using solution feedstocks in the thermal spray deposition process. This permits tailored engineering of the interfaces at a finer length scale by compositional and microstructural grading throughout the entire coating thickness. This process permits an efficient conversion of molecules-atoms

(solution dependent) into aerosol droplets and subsequent chemical reactions to form the product layers on the substrate. With post-deposition treatment of the as-synthesized coating, there can be optimized microstructures, structures, density and adhesion.

- 5 By using thermal spraying of solution precursor feedstocks, compositionally and microstructurally graded coatings are fabricated which have unique advantages. The molecular level mixing of the constituents in solution precursor feedstocks allows for better chemical homogeneity of sprayed products. By using fine droplets that are many times smaller than the conventionally used powder feedstock (e.g. 30 microns or
10 larger in particle size), a finer scale of microstructure can be achieved. The solidification of droplets can be controlled in flight or on impact on the substrate by controlling the spray temperature, the working distance and the substrate temperature. This provides a means to reduce the size of microstructure as compared to the powder feedstock routes. Finally, functional grading of multilayered coatings can be achieved
15 at a much finer scale, particularly for nanostructured graded coatings, both compositionally and microstructurally, compared to the powder feedstock approach wherein the size of splat poses a limit on the scale of mixing and grading. Functional grading may include, but is not limited to, the graded continuous interface where the microstructure, structure and chemistry of two or more materials are varied
20 continuously. Such grading may enhance the thermal, chemical and mechanical stability of multilayered coatings and the control of the mechanical, electrical, magnetic and other transport properties.

Brief Description of the Drawings

Fig. 1 illustrates a schematic diagram for the coating process.

- 25 Fig. 2 illustrates a gradient coating in the form of a graph showing the relative concentrations of the two components A and B as a function of the distance from the substrate S.

Description of the Preferred Embodiments

As shown schematically in Fig. 1, a thermal spray coating apparatus such as the Metco 9MB-plasma torch can be fitted with a GH nozzle, and the powder injection port is removed and replaced with multiple injection nozzles which are incorporated and arranged with para-axial or oblique angle injection into the plasma flame. As seen in Fig. 1, the thermal spray gun 10 has a flame generating tube 12 from which the flame 13 extends. Adjacent the flame is the liquid supply chamber 14 which will direct the liquid into the flame. The multiple injection nozzles 16 in the chamber 14 permit controlled and varying amounts of the various component feedstock solutions to be applied to the plasma spray gun. The coating mixture is then sent through the flame and onto the substrate 18. This setup can be mounted on a 6-axis GM-Fanuc robot. A high-pressure chemical metering pump can be used to feed the solutions to the nozzles. Preferably, the primary and secondary arc gases are argon and hydrogen respectively, and the atomization gas is nitrogen.

Deposition of ceramic coatings using solution feedstocks can be made with coatings greater than or equal to 40 microns thick of alumina, zirconia, yttria stabilized zirconia, as well as compositionally graded alumina-zirconia-alumina and graded alumina-yttria stabilized zirconia on stainless steel substrates. The feedstocks include aqueous solution of aluminum nitrate, alcohol-water solution of aluminum tri-sec butoxide, alcohol-water solution of zirconium n-propoxide, and alcohol-water solution of yttrium nitrate and zirconium n-propoxide. Thinner coatings can also be made by running a fewer number of thermal spray passes over the substrate. The solution precursors may include organometallic, polymeric, and inorganic salts materials, which should be cost efficient for a particular deposition. Preferred inorganic salts are nitrates, chlorides and acetates.

Adherent and smooth coatings can be prepared, depending on the specific deposition conditions such as spray working distance. Characterization of coatings' structure, microstructure, and adhesion included analysis by x-ray diffraction, scanning electron microscopy and energy dispersive spectroscopy.

Post deposition techniques may include conventional furnace heat treatment, UV lamp, laser, microwave, and other beam sources at various wavelengths. The post deposition techniques may also be employed simultaneously, or in sequence, during cycles of thermal spraying of the liquid precursors, so as to control the microstructure, structure, chemistry and interfaces properties, and porosity etc.

Fig. 2 illustrates a substrate, S, on the left to which a coating of components A and B have been added as a gradient coating. The two curved lines indicate the % of each component in the total coating at each height above the substrate. Initially, at the substrate surface, the only coating component is A and the amount of B is zero. Then as the spray coating continues to build up the coating, more of B is added until, when the height in region 2 is reached, the concentration of each component is about the same. This trend of increasing the relative amount of B continues until at region 3, the composition is all B. Finally, the third coating layer is built by increasing the A component until it is all A in region 5.

Fig. 2 illustrates how the gradient can be finely controlled to change from one composition to another by using the solution precursors. The three component layer shown in Fig. 2 also illustrates how the three layers can be built up with good adherence between the layers due to the gradient transition between them. When coating A is alumina, it provides good adherence to the substrate. When coating B is zirconia, it provides thermal resistance properties. By applying a second layer of A of alumina, it provides oxygen protection to the intermediate zirconia layer. Such a concept of graded coatings can be used in other applications as well and by using other materials.

As seen in Fig. 1, the thermal spray apparatus can have a series of injection nozzles in the spray gun mechanism to deliver the various combination of liquid coating components. Alternative spraying devices could be used in which two spray guns could be positioned side by side to deliver two separate compositions, or other combinations of multiple guns can be used.

In another embodiment, it is possible to add small pre-formed particles to the liquid feedstock solution as suspended particles. When co-spraying the suspended particles together with the same liquid carrier, it is preferred to add a surfactant which allows the nanostructured particles to be somewhat agglomerated to only a few
5 microns, but definitely smaller than the conventional 30 or larger micron agglomerate size. This embodiment is useful when applying materials that are not stable in the liquid state, or when applying two components A and B where they would be undesirably reactive in the liquid state while they were being applied.

By using the process of this invention, the coating artisan is given the capability
10 of making thin or thick coatings which are made of nanostructured particles which have a diameter of less than about 100 nm (0.1 micron). Each layer can be as thin as about 100 nm, but the particle size (or crystallite size) in each layer must be less than 100 nm.

Conventional thermal spraying of thick coating will only give particles of at least several microns in one dimension, i.e. the thickness of the splat. Even
15 electroplating is not a straight forward procedure for grading, since the conductivities of different species vary normally, and thus result in non-stoichiometric deposition.

Examples

Having described the basic aspects of the invention, the following examples are given to illustrate specific embodiments thereof.

20 Example 1

This example illustrates the production of a multilayer coating according to the present invention.

The following solutions were used as the feedstocks: 0.5 M aluminum nitrate (AN); 0.5 M aluminum tri-sec- butoxide (ASB); 0.5 M zirconium n-propoxide; and 0.5
25 M zirconium n-propoxide with 4 wt% yttria. The alkoxide solutions were made by dissolving the alkoxide in an ethanol-acetic acid solution and then adding water. The aluminum nitrate solution was prepared by dissolving the appropriate amount of the salt in distilled deionized water. The nitrate has the advantage of being very inexpensive, and there are no undesirable secondary reactions. However, the nitrate has

been suggested to interfere with the stabilization of zirconia, and if large amounts of solution are used the NO_x ($x=1, 2$) from the decomposition of the nitrate may be a problem. The alkoxide, on the other hand, is more expensive as compared to the nitrate (but the amount of alumina is not the major component) and the alkoxide is reactive
 5 with water. It has been shown to stabilize zirconia at 10%.

The graded sample was prepared by spraying 20 passes of the aluminum nitrate solution, stopping and then running distilled water through the line to remove the AN solution. This was sprayed into a bucket and not on the substrate. Then, the solution was changed to zirconia (unstabilized) and sprayed until the ZrO_2 sol had replaced the
 10 water. Then, the plasma was started and the 20 passes were sprayed on the substrate. Again, the system was flushed with water and the AN sol was used again. The result was a graded coating of alumina-zirconia-alumina on a steel substrate as characterized by Run 1a in Table 1. The crystallite size was obtained by x-ray line broadening, and the microstructure by scanning electron microscopy. The chemistry was characterized
 15 by energy dispersive x-ray spectroscopy.

Table 1

Run	Solution feedstock	Phase of deposited coatings	Average crystallite size (nm)
1a	Graded AN-ZP-AN	monoclinic ZrO_2	19
		tetragonal ZrO_2	25
		alpha alumina	37
1b	aluminum nitrate (AN)	gamma alumina	14
20 1c	aluminum sec-butoxide (ASB)	gamma alumina	67
1d	yttria stabilized Zr n-propoxide (ZP)	tetragonal ZrO_2	42

For Run 1a, the two alumina layers had an average crystallite size of 37 nm. For the intermediate zirconia layer, there were two phases present.

Additional runs were made with three solutions as set forth in Runs 1b-1d in Table 1. All of the average crystallite sizes were less than 80 nm. The data shows that nanostructured coatings were fabricated.

The difference in the nature of the alumina layer in Runs 1a and 1b is due to the existence of Zr which acts as a thermal barrier. Most of the heat is trapped in the Zr layer, and so it allows a higher temperature phase of alumina to be formed in Run 1a. In Run 1b, most of the heat is conducted away to the substrate so that a low temperature phase of alumina is formed.

Example 2

A systematic investigation of coating parameters was carried out. All solutions were prepared from aluminum nitrate at the molar concentration given in Table 2. Samples were characterized by XRD if the coating adhered to the substrate.

In the following Table 2, the relative plasma temperature was determined by measuring by the current in amperes divided by the gas flow in standard cubic feet per hour. The aluminum nitrate concentration is measured in moles/liter and the speed is in mm/sec. The spray distance is in inches and the term "OOR" indicates that the grain size was "out of range" meaning that it was larger than 100 nm.

Table 2

Sample No.	Plasma Temp (A/SCFH)	particle size	concentration	speed	spray distance	Grain Size (nm)	phase	Adhere
1a	6.875	0	0.5	20	1.5	17	gamma	Y
1b	6.875	0	0.5	20	2	97	gamma	Y
1c	6.875	0	0.5	20	2.5	OOR	gamma	Y
1d	6.875	0	0.5	20	3			N
2a	6.875	0	1.25	1000	1.5			N
2b	6.875	0	1.25	1000	2			N
2c	6.875	0	1.25	1000	2.5			N
2d	6.875	0	1.25	1000	3			N
3a	6.875	35	0.5	1000	1.5			N

Sample No.	Plasma Temp (A/SCFH)	particle size	concentration	speed	spray distance	Grain Size (nm)	phase	Adhere
3b	6.875	35	0.5	1000	2			N
3c	6.875	35	0.5	1000	2.5			N
3d	6.875	35	0.5	1000	3			N
4a	6.875	35	1.25	20	1.5			N
4b	6.875	35	1.25	20	2			N
4c	6.875	35	1.25	20	2.5			N
4d	6.875	35	1.25	20	3			N
5a	8.125	0	0.5	1000	1.5	29	gamma	Y
5b	8.125	0	0.5	1000	2			N
5c	8.125	0	0.5	1000	2.5			N
5d	8.125	0	0.5	1000	3			N
6a	8.125	0	1.25	20	1.5	OOR	alpha	Y
6b	8.125	0	1.25	20	2	135 18	alpha gamma	Y
6c	8.125	0	1.25	20	2.5	15	gamma	Y
6d	8.125	0	1.25	20	3	37	gamma	Y
7a	8.125	35	0.5	20	1.5	28	gamma	Y
7b	8.125	35	0.5	20	2			N
7c	8.125	35	0.5	20	2.5	30	gamma	Y
7d	8.125	35	0.5	20	3	30	gamma	Y
8a	8.125	35	1.25	1000	1.5			N
8b	8.125	35	1.25	1000	2	38	gamma	Y
8c	8.125	35	1.25	1000	2.5			N
8d	8.125	35	1.25	1000	3	37	gamma	Y

Qualitative observations can be made from the data in Table 2. First, the adhesion of the liquid coating is generally better than when spraying the particles themselves because the particles did not have enough thermal energy to form a true bonding with the substrate or with themselves under the same conditions as the liquid spray. Second, the table demonstrates the need for careful control of parameters to optimize the coating.

Example 3

Investigation of grading composition was carried out using six premixed solutions of aluminum sec butoxide (ASB) and zirconium n-propoxide (ZP), using volume ratios of a total volume of 100 mL as set forth in Table 3.

Table 3

Coating	ASB %	ZP %
1	100	0
2	90	10
3	70	30
4	50	50
5	30	70
6	10	90

The deposition time (t) (as measured by the time the solution was passed through the gun) and the working distance (D) between the gun and substrate were investigated and the results are set forth in Table 4.

Table 4

Run No.	Time & distance	Phase(s) detected Major phase listed first	Average Crystallite Size (nm)
1	t: 1 min D: 1"	Tetragonal ZrO ₂ Monoclinic ZrO ₂ alumina	12 8 2
2	t: 1 min D: 2"	Tetragonal ZrO ₂ Monoclinic ZrO ₂ alumina	21 17 15
3	t: 1.5 min D: 1"	Tetragonal ZrO ₂ Monoclinic ZrO ₂ alumina	20 19 43
4	t: 1.5 min D: 2"	Tetragonal ZrO ₂ alumina	10 4
5	t: 2 min D: 1"	Monoclinic ZrO ₂ Tetragonal ZrO ₂ alumina	58 59 13
6	t: 2 min D: 1.5"	Tetragonal ZrO ₂ Monoclinic ZrO ₂ alumina	17 14 45
7	t: 2 min D: 2"	Tetragonal ZrO ₂ alumina	11 11

The alumina phase matches JCPDS card 37-1462 (from coprecipitated mixture at 500°C). This may suggest that nucleation of low temperature alumina phase at the surface of substrate, which is different from the high temperature deposition of molten alumina particles in conventional thermal spraying.

It is understood that the foregoing detailed description is given merely by way of illustration and that many variations may be made therein without departing from the spirit of this invention.

What is claimed is:

CLAIM 1. A method of forming a thin film or coating made of nanostructured particles having a particle size less than 100 nm, the method comprising the step of thermally spraying a solution of a liquid coating precursor feedstock onto a substrate to form said film or coating.

CLAIM 2. The method of Claim 1, wherein the thin film or coating has a thickness of about 100 nanometers or larger.

CLAIM 3. The method of Claim 1, wherein the thin film or coating is made of more than one layer by thermally spraying different precursor feedstock solutions.

CLAIM 4. The method of Claim 1, wherein the composition of the precursor feedstock is varied to form a composition gradient coating having nanoparticle size particles of less than 100 nm.

CLAIM 5. The method of Claim 1, wherein the thin film or coating materials are selected from the group consisting of ceramics-ceramics; metal-ceramics; metal-metal; organic-inorganic and mixtures thereof.

CLAIM 6. The method of Claim 1, wherein an external energy source is applied during the coating process or during a post deposition period to modify the coating.

CLAIM 7. The method of Claim 1, wherein the temperature of the thermal spraying is controlled so that the liquid feedstock is not vaporized before it reaches the substrate.

CLAIM 8. The method of Claim 1, wherein the coating precursor feedstock is selected from the group consisting of an aqueous solution of aluminum nitrate, an alcohol-water solution of aluminum tri-secbutoxide, and alcohol-water solution of zirconium n-propoxide, an alcohol-water solution yttrium nitrate and zirconium n-propoxide, and mixtures thereof.

CLAIM 9. The method of Claim 3, wherein the different precursor feedstock solutions are sequentially applied in the same thermal plasma spray apparatus.

CLAIM 10. The method of Claim 1, wherein the coating precursor feedstock further comprises suspended particles.

CLAIM 11. The method of claim 11, wherein the suspended particles are nanostructured particles.

CLAIM 12. The method of Claim 11, wherein the coating precursor feedstock further comprises a surfactant to allow the nanostructured particles to be somewhat agglomerated to only a few microns.

CLAIM 13. The method of Claim 1, wherein the droplet size of the solution feedstock is controlled and varied.

CLAIM 14. The method of Claim 13, wherein the droplet size is reduce by placing a fine screen mesh between the spray nozzle and the substrate.

CLAIM 15. The method of Claim 1, wherein the residence time, the in-flight temperature of droplet, and the working distance to the substrate are controlled to control the structure and the microstructure of the deposited coatings.

CLAIM 16. The method of Claim 1, wherein the spraying is controlled so that fine droplets are allowed to solidify before reaching the substrate by controlling the in-flight temperature whereby the resulting splat will have a smaller dimension compared to that obtained by using a powder feedstock.

CLAIM 17. The method of Claim 1, wherein the spraying is controlled so that the droplets are allowed to reach the substrate in the liquid state whereby solidification of droplets at the substrate will also lead to finer splat microstructure and better chemical mixing when more than a single phase of materials are sprayed.

CLAIM 18. A thin film or coating on a substrate made of nanostructured particles which have a particle size of less than 100 nm.

CLAIM 19. A thin film or coated material made by the method of Claim 1 having a nanostructured material with a particle size of less than 100 nm.

CLAIM 20. A multilayer thin film or coated material made by the method of Claim 3, having a nanostructured material with a particle size of less than 100 nm.

CLAIM 21. The multilayered thin film or coated material of Claim 20, having a nanostructured graded material and fine scale grading, both compositionally and microstructurally.


CLAIM 22. The multilayered thin film or coated material of Claim 21, wherein the layers are integrated by gradually graded interfaces rather than abrupt interfaces so as to permit the compatibility of hybrid multilayered materials.


CLAIM 23. The multilayered coated material of Claim 22, wherein the hybrid multilayered materials are selected from the group consisting of ceramics-ceramics; metal-ceramics; metal-metal; organic-inorganic and mixtures thereof.

CLAIM 24. The multilayered coated material of Claim 21, wherein the grading is microstructural, structural and chemical with continuous interfaces at a fine scale.

CLAIM 25. A graded thin film or coated material made by the method of Claim 4, having a nanostructured graded material and fine scale grading, both compositionally and microstructurally.

FIG. 1



*FIG. 2*

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/14912

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C23C4/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C23C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 97 18341 A (THE UNIVERSITY OF CONNECTICUT) 22 May 1997 (1997-05-22) claims 10-30; examples 3-8 ---	1-5, 7-10, 18-25
A	FR 1 393 487 A (COMPAGNIE GÉNÉRALE D'ÉLECTRICITÉ) 7 July 1965 (1965-07-07) page 2, column 1, line 21 - line 24; claims A-C; figure 1 ---	1, 3, 5, 8, 9
A	HULL P J ET AL: "SYNTHESIS OF NANOMETER-SCALE SILVER CRYSTALLITES VIA A ROOM-TEMPERATURE ELECTROSTATIC SPRAYING PROCESS" ADVANCED MATERIALS, vol. 9, no. 5, 1 April 1997 (1997-04-01), pages 413-417, XP000683893 ISSN: 0935-9648 ---	1, 18
	-/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

6 October 1999

Date of mailing of the international search report

14/10/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Elsen, D

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/14912

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9718341 A	22-05-1997	CA 2237588 A CN 1175984 A EP 0866885 A	22-05-1997 11-03-1998 30-09-1998
FR 1393487 A	07-07-1965	NONE	
US 5688565 A	18-11-1997	US 5519234 A US 5456945 A US 5138520 A US 5723171 A CA 2145878 A DE 69307533 D EP 0665814 A JP 8502946 T WO 9410084 A US 5514822 A US 5620739 A US 5723361 A US 5624707 A US 5614018 A US 5516363 A US 5540772 A US 5888583 A US 5559260 A US 5614252 A US 5654456 A US 5759923 A US 5909042 A US 5871853 A US 5814849 A US 5690727 A AU 2013992 A JP 11131247 A JP 2860505 B JP 6508659 T US 5434102 A WO 9215112 A US 5468679 A US 5825057 A US 5439845 A US 5316579 A US 5423285 A AU 636818 B AU 4846990 A JP 4502939 T WO 9007390 A US 5119760 A AU 3273893 A CA 2145879 A DE 4395687 T EP 0616726 A EP 0665981 A JP 7502150 T JP 8502628 T JP 8502859 T	21-05-1996 10-10-1995 11-08-1992 03-03-1998 11-05-1994 27-02-1997 09-08-1995 02-04-1996 11-05-1994 07-05-1996 15-04-1997 03-03-1998 29-04-1997 25-03-1997 14-05-1996 30-07-1996 30-03-1999 24-09-1996 25-03-1997 05-08-1997 02-06-1998 01-06-1999 16-02-1999 29-09-1998 25-11-1997 15-09-1992 18-05-1999 24-02-1999 29-09-1994 18-07-1995 03-09-1992 21-11-1996 20-10-1998 08-08-1995 31-05-1994 13-06-1995 06-05-1993 01-08-1990 28-05-1992 12-07-1990 09-06-1992 19-07-1993 11-05-1994 23-11-1995 28-09-1994 09-08-1995 02-03-1995 19-03-1996 26-03-1996
JP 63121647 A	25-05-1988	NONE	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/14912

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR 1480209 A	31-07-1967	NONE	